## Declaration of performance

Nr. 2023-006

## **LOWIE** BRICKS

## 1. Product type: Lowie CLASSIC HV WF 2. Intended use Masonry bricks 3. Name & address manufacturer: Lowie Bricks, Ropswalle 13 8930 Menen

5. Declared performances:		
Essential features	performance	
Dimensions	210X80X50	
Flatness of facing sides	< 2,5 mm	
Flatness of bed sides	< 0,5 mm	
Planparallel bed sides	< 1 mm	
Mechanical strength after 14 days	> 10 N/mm2	
Mechanical strength after 28 days	+- 20 N/mm2	
Expansion/shrinkage	< 0,45 mm/m	
Insulation value (50/50)	0,71 W/m*K	
Gross dry volume mass	1690 KG/M3	
Fire resistance	A1	
Durability (freeze/thaw)	F2	
Total water absorption	<16%	
Initial water absorption	[2-6] kg/(m2min)	

Storage & Processing	Sawing
-Place on a flat surface and cover	Dry sawing may release dust. This dust will contain
	silicon or quartz particles that can be harmful to
-Mix multiple packs	health. Anyone performing such work is advised to
- Follow the Lowie Bricks processing instructions	wear FFP3 dust masks.

Each pack contains 33% bricks with a painted header. These can be kept separate and used specifically in corner applications or locations where the header is visible.